

MAR 3016/2

Martindale



Martindale

For assessing rub fastness of textiles in conformity with DIN EN ISO 12947-1/2/3/4 April 2007. The round sample is rubbed against a standard cloth under a defined load following a predefined pattern (Lissajous curve). The rub fastness is then determined against the time interval when the textile sample is destroyed. Each workstation of this ten-station machine can be individually set up for testing. Operation by touch screen.

Technical Data

Footprint: 1000 × 800 mm
Supply voltage: 230 V Supply frequency: 50 Hz
Power consumption: approx. 800 W
Compressed air supply: 6 bar

Reference N° **MAR 3016/2**

Phone: +49 6331 2490 0, E-Mail: peter.schultheis@pfi-germany.com